This Page Is Inserted by IFW Operations and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents will not correct images, please do not report the images to the Image Problem Mailbox.

CLAIMS

1. A non-aqueous electrolyte secondary battery comprising a chargeable and dischargeable positive electrode, a non-aqueous electrolyte containing a lithium salt, and a chargeable and dischargeable negative electrode,

wherein at least one of said positive electrode, said non-aqueous electrolyte and said negative electrode contains at least one selected from the group consisting of

a phosphate represented by the general formula (1):

$$\begin{array}{c|c}
O R^{1a} \\
 & \\
O = P - O R^{2a}
\end{array}$$

$$\begin{array}{c}
O R^{3a}
\end{array}$$


where R^{1a} , R^{2a} and R^{3a} independently represent an aliphatic hydrocarbon group having 7 to 12 carbon atoms,

a phosphate represented by the general formula (2):

$$\begin{array}{c|c}
OR^{16} \\
| \\
O = P - OR^{26} \\
| \\
OH
\end{array}$$
(2)

where R^{1b} and R^{2b} independently represent an aliphatic hydrocarbon group having 1 to 12 carbon atoms or an aromatic hydrocarbon group, and

a phosphate represented by the general formula (3):



where R^{1c} represents an aliphatic hydrocarbon group having 1 to 12 carbon atoms or an aromatic hydrocarbon group.

2. The non-aqueous electrolyte secondary battery in accordance with claim 1,

wherein at least two selected from the group consisting of R^{1a} , R^{2a} and R^{3a} are identical with each other in said general formula (1), and or R^{1b} and R^{2b} are identical with each other in said general formula (2).

3. The non-aqueous electrolyte secondary battery in accordance with claim 1,

wherein at least one of said positive electrode, said non-aqueous electrolyte and said negative electrode contains a mixture of at least two selected from the group consisting of a phosphate represented by said general formula (1), a phosphate represented by said general formula (2), and a phosphate represented by said general formula (3), where R^{1a}, R^{2a} and R^{3a}, R^{1b}, R^{2b} and R^{1c} in said general formulae (1) to (3) have the same number of carbon atoms, respectively.

4. The non-aqueous electrolyte secondary battery in accordance with claim 3,

wherein the percentage by volume of each of said

Ø

phosphates in said mixture is not less than 30%.

5. The non-aqueous electrolyte secondary battery in accordance with claim 1,

wherein at least one of said positive electrode, said non-aqueous electrolyte and said negative electrode contains at least one phosphate selected from the group consisting of dibutyl phosphate, dipentyl phosphate, dihexyl phosphate, dihexyl phosphate, dihexyl phosphate, dinonyl phosphate, didecyl phosphate, didecyl phosphate, didecyl phosphate, didecyl phosphate, monobutyl phosphate, monobutyl phosphate, monobetyl phosphate, monoctyl phosphate, monononyl phosphate, monodecyl phosphate, monodecyl phosphate, monododecyl phosphate.

6. The non-aqueous electrolyte secondary battery in accordance with claim 1,

wherein said non-aqueous electrolyte contains 0.1 to 20 wt% of said phosphate.

7. The non-aqueous electrolyte secondary battery in accordance with claim 1.

wherein said chargeable and dischargeable positive electrode contains at least one selected from the group consisting of LiCoO₂, LiMn₂O₄, LiNiO₂ and LiFeO₂, and said chargeable and dischargeable negative electrode contains at least one selected from the group consisting of a carbon material, a metallic lithium, a lithium alloy and a compound containing lithium.

N

8. A method for producing a non-aqueous electrolyte secondary battery comprising the steps of:


preparing an electrode mixture comprising an active material, a conductive agent and a binder,

applying said electrode mixture on a current collector plate to prepare an electrode,

assembling a non-aqueous electrolyte secondary battery using said electrode and a non-aqueous electrolyte and,

adding at least one of said active material, said electrode mixture and said electrode with at least one selected from the group consisting of

a phosphate represented by the general formula (1):




where R^{1a} , R^{2a} and R^{3a} independently represent an aliphatic hydrocarbon group having 7 to 12 carbon atoms,

a phosphate represented by the general formula (2):

where R^{1b} and R^{2b} independently represent an aliphatic

hydrocarbon group having 1 to 12 carbon atoms or an aromatic hydrocarbon group, and

a phosphate represented by the general formula (3):



where R^{1c} represents an aliphatic hydrocarbon group having 1 to 12 carbon atoms or an aromatic hydrocarbon group.